

SPECIFICATION SECTION 09 67 23 – RESINOUS FLOORING

PART 1 – GENERAL

1. **SECTION INCLUDES**
 - A. This section includes the following resinous flooring system.
 1. Seamless Urethane Floor System: Integrated system for floors consisting of 100% solids urethane cement.
2. **REFERENCE STANDARDS**
 - A. ASTM F 2170 | Standard Test Method for Determining Relative Humidity in Concrete Slabs Using in situ Probes.
 - B. ICRI No. 03732 | Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays, CSP 1-9.
 - C. PDCA Standards 1-24.
 - D. EPA Method 24.
3. **ADMINISTRATIVE REQUIREMENTS**
 - A. Pre-installation Meeting. Prior to the installation of the specified system, a meeting shall be held at the project site with the manufacturer's representative, the installer, the engineer/architect, general contractor, and the Owner's representative. General Contractor to document meeting discussions and furnish a copy to each participant. Meeting topics to include, but not be limited to:
 1. Planned start and completion timing for each mobilization.
 2. Safety procedures.
 3. Coordination of other trades in the area.
 4. Existing and new slab conditions.
 5. To discuss required testing.
 6. Existing substrate conditions.
 7. Surface preparation.
 8. Required environmental conditions.
 9. Installation sequencing and cure times.
 10. Protection of completed work.
4. **SUBMITTALS**
 - A. With bid proposal
 1. List of no less than five (5) projects of similar size and complexity, using the approved coating systems, including Owner's names, contract amount, contact numbers, date of substantial completion.
 2. Manufacturer's data on specified products, describing physical and performance characteristics; sizes, patterns and colors available.
 3. Written verification from local distributor that installer is versed on Polymer Nation system specified.
 4. Failure to provide the above noted submittals shall cause bid to be rejected.
 - B. Upon Contract
 1. Product Data. For each product to be used in the system, include manufacturer's technical data sheet, application instructions and SDS.
 2. Provide pertinent Detail Drawings including terminations, keyways, cove etc.

SPECIFICATION SECTION 09 67 23 – RESINOUS FLOORING

3. Samples. For each resinous system specified herein, provide, when requested, two samples applied to a rigid backing, minimum size 12" X 12".
 4. Additional LEED Submittals if required to meet project design requirements.
5. **QUALITY ASSURANCE**
- A. Source Limitations. Obtain all resinous materials, including waterproofing membranes, grouts, resins, curing agents, grout coats, aggregates, topcoats, patching and fill materials, joint sealants, and repair materials from a single manufacturer.
 - B. Manufacturer Field Services.
 1. The installer of the coating system shall contact the material manufacturer during the bidding phase of the project and shall include in the cost of his bid proposal, the cost of a manufacturer's representative to be present throughout the duration of all aspects of the work specified in this Section.
 2. Material Manufacturer shall document and verify that all conditions are acceptable prior to commencement of each installation phase. This documentation must be included with the final warranty.
6. **MOCKUP**
- A. Apply a mockup of each coating system to establish a benchmark of finish, thickness, texture, process, color, and quality.
 - B. Apply a mockup of each coating system to establish a benchmark of finish, thickness, texture, process, color, and quality.
 1. Mockup shall be applied to the specified substrate(s).
 2. Mockup shall be no larger than 100 square feet.
 3. Approved mockups may become part of completed Work if undisturbed at the time of Substantial Completion.
 4. If a cove base is to be included on the project, mockup shall include the same.
 5. Cost of mockup shall be included in bid proposal.
 6. Install mockup, as directed by Owner's representative, in properly lighted area.
 7. Do not proceed with work prior to receipt of written acceptance of mock-up.
7. **DELIVERY, STORAGE & HANDLING**
- A. Materials shall be delivered in original packages and containers, with seals unbroken, bearing manufacturer's labels indicating brand name and directions for storage and mixing with other components.
 - B. Store materials in a location to prevent deleterious effects from sunlight, moisture, excessive heat, or cold.
 - C. Storage of materials shall comply with all fire and safety regulations.
8. **PROJECT CONDITIONS**
- A. Environmental Limitations. Comply with coatings manufacturer's technical data sheet for acceptable substrate and ambient temperatures, concrete moisture levels, ventilation, and other environmental conditions that may negatively affect resinous flooring application or performance.
 - B. Lighting. Proper lighting is required for installation. When possible, lighting shall simulate permanent lighting conditions during coatings application and is the responsibility of the Owner or General Contractor to provide.

SPECIFICATION SECTION 09 67 23 – RESINOUS FLOORING

- C. Installation. Close spaces to traffic during coatings application and for not less than 48-hours after application unless manufacturer recommends a longer period.
- D. Airborne Contamination. Coating systems should not be applied in areas where excessive dust or other airborne particulate matter may generate an unacceptable finish.
- E. Install coatings only when environment meets coating manufactures requirements and for 72 hours prior to, during and 24 hours after installation of material.

PART 2 – PRODUCTS

2.01 MANUFACTURERS

- A. Manufacturer
 - 1. Polymer Nation, Waukegan, IL basis of design sales@polymernation.com FLORIDA
CONTACT : Floor Coating Source, Jon Lopez, 239-424-8692, info@floorcoatingsource.com
 - 2. Proposed substitutions must be equivalent or superior to basis of design materials in performance, history of use, layers, and overall system thickness.
 - 3. All substitution requests must be received 14 days prior to bid date and must be approved by architect, via addenda, prior to bid date.
 - 4. No substitutions will be considered without written approval from architect.

2.02 SYSTEM

- A. Seamless Epoxy Floor System, consisting of 100% solids urethane cement.
 - 1. Deco-Guard 241 as manufactured by Polymer Nation.
 - 2. System Characteristics/Performance Requirements:
 - a) Color and Pattern. As selected by Owner from manufacturer's full range.
 - b) Wearing Floor Surface. Textured for slip-resistance per Owner selection from manufacturer's full range.
 - c) Cove Base. Per room finish schedule if required.
 - d) System Thickness. 3/16th
 - e) VOC's. <50 g/lt per EPA Method 24 for each component.
 - f) Product Composition. 100% solids urethane mortar.
 - g) High or Low Solids solvent based, and all water-based systems excluded.
 - 3. System Components
 - a) Filler material: SP-15
 - b) Body Coat: F-52 SL 36 with # 1322 broadcast aggregate
 - c) Wear Coat:F-52 D
 - 4. General Performance Requirements.
 - a) Resinous flooring system shall meet minimum published standards in accordance with Polymer Nation products as specified in this Section.

PART 3 – EXECUTION

3.01 EXAMINATION

- A. Testing of Floor Slabs.
 - 1. Prior to the installation of resinous flooring, concrete should be tested for moisture content that could be detrimental to the long-term adhesion of coating materials. Tests below must be completed in accordance with the most recently revised Test Methods:
 - a) Relative Humidity [in situ] Testing per ASTM F 2170

SPECIFICATION SECTION 09 67 23 – RESINOUS FLOORING

- b) Others as required by manufacturer or unique job conditions. If additional testing is required, additional costs may be incurred by Owner.
2. The relative humidity in the specific location of the application shall be equal to or less than 75%. If installer obtains a result above 75% relative humidity, contact your local Polymer Nation representative for further instructions.

3.02 PREPARATION

- A. General. Prepare and clean substrates in accordance with manufacturer's written instructions for substrate indicated.
- B. Concrete Floors. Concrete must be free of laitance, glaze, efflorescence, curing compounds, form-release agents, dust, dirt, grease, oil, and other contaminants, incompatible with floor coatings. Floor slabs shall be prepared as follows:
 1. Prepare per ICRI CSP 3-5, and diamond grind edges as required.
 2. Remove and legally dispose of all debris and contaminants generated by the surface preparation process.
 3. Steel media resulting from the shot blasted floor slab surface shall be removed from cracks, slab edges, construction joints, and corners by magnetic broom, vacuum, or stiff bristle broom.
 4. Chase cracks, non-moving joints with appropriate diamond blades.
 5. Cut and prepare keyway terminations per manufacturer's detailed drawings.

3.03 INSTALLATION

- A. General.
 1. Apply components of resinous coating system according to manufacturer's written instructions to produce a uniform, monolithic wearing surface at the specified thickness.
 2. Coordinate application of components to provide optimum adhesion of resinous floor system to substrate.
- B. Installation.
 1. Prefill non-moving cracks, joints and keyways as needed to promote smooth floor transitions and terminations.
 2. INTEGRAL COVE BASE: (If applicable)
Apply cove strip to wall at desired height to provide a finished top for the cove. Mix cove material per manufacturer's instructions and apply to the wall to match the approved mockup.
 3. Apply body coat at 125 mils WFT. Spike roll to assist in leveling and air release.
 4. Broadcast aggregate into wet Body Coat until rejection making sure to use even distribution and avoid piles and clumps. A full broadcast will result in 3/16" floor thickness.
 5. Remove all loose broadcast material by sweeping and vacuum.
 6. Apply Wear Coat at 16-20 mils WFT.
 7. Cut and fill dynamic joints as required.

3.04 CURING

- A. Cure resinous flooring components according to manufacturer's written instructions.
 1. Temperatures shall be maintained at 65°F - 85°F with less than 50% relative humidity.
 2. Water leaks must be prevented as they may damage finish sheen.
 3. Prevent contamination during curing processes.

SPECIFICATION SECTION 09 67 23 – RESINOUS FLOORING

3.05 CLEANING

- A. Work area shall be left clean.
- B. Remove all trash from work area.
- C. Consult coating manufacture for recommended cleaning materials and procedures.

3.06 WARRANTY

- A. Polymer Nation warrants that material shipped to buyers at the time of shipment are substantially free from material defects and will perform substantially to Polymer Nations published literature if used in accordance with the latest prescribed procedures and prior to the expiration date.
- B. Polymer Nation liability with respect to this warranty is strictly limited to the value of the material purchase.

END OF SECTION